

Amendments to the Specification

Please replace the paragraph beginning at page 14, line 15 with the following rewritten paragraph:

[0001] A steel product according to the invention may have a bake hardening BH2 higher than 40MPa in both longitudinal and transversal directions. BH2 values express the difference between the yield strength of a sample that has undergone controlled ageing and 2% prestrain, and the yield strength of said same sample having undergone a controlled baking step (details of all the various steps are set out in the norm SEW094).